

B110C

Ultra Durable

Resin • Flat head

- Higher heat resistance up to 150°C
- Good chemical and solvent resistance
- High resolution for 300 - 600 dpi printer
- Applicable to a wide range of synthetic materials: PET/PP/PE/PVC films...
- Ricoh's unique coating on the back allows reliable and superior matching qualities with the thermal head

PRINTING PROPERTIES

Maximum printing speed 4 IPS

	Non coated paper	Top-coated paper	PET	PE	PP	PVC
Compatibility	✗	✗	✓	✓	✓	✓
Image density	-	-	1.53	1.57	1.57	1.46

Note: Smoothness Bekk for paper family must be over 2000s.

Image resolution for paper & film:

Minimum size: - For the lines: 0.1mm - For the characters: 1.0mm

RIBBON PROPERTIES

- Total ribbon thickness: < 9 µm
- Polyester film thickness: 4.5 µm
- Friction coefficient: < 0.045
- Ink melting point: 83°C
- Tearing resistance: > 200N/mm²
- Transmission density: 1.00 mini

CERTIFICATES/ DIRECTIVES

TSCA ✓
Toxic Substance Control Act

RoHS ✓
Restriction of Hazardous Substances

WEEE ✓
Waste Electrical & Electronic Equipment

REACH ✓
Chemical & Environment

ISO EN71-3 ✓
European Standard EN71

2003/11/EC ✓
Directive 2003/11/EC

2000/53/EC ✓
Directive 2000/53/EC

76/769/EEC ✓
Directive 76/769/EEC

Application



Automotive



Electronics



Heat resistance

GENERAL CONDITION

Usage conditions: 5 to 35°C at 30 to 85% of relative humidity.

Storage conditions: Keep indoor avoiding high temperature, high humidity, direct sunlight.

Storage life: 24 months after slitting day.


RICOH
imagine. change.

PRINTED IMAGE DURABILITY

TESTS	RESULT	B110C with standard white polyester
Smear + heat 100°C	ANSI > B	
Smear with cardboard (weight 1kg - 50 back & forwards)		Engine oil 250
Heat (200°C)	No ink on the cotton fabric	Brakefluid 70
Heat gradient 3.6kgF/cm ²		Windshieldwasher 250
Scratch	ANSI > B	Diesel 250
50 back and forwards with a rub tester		Unleaded petrol 160
Light	ANSI A	IPA 250
Xenon lamp at 650W/m ²		Ethanol 180
Water	ANSI A	
24 hours in water		

Back & forwards until beginning of erase

B110C DURABILITY



5: No damage
0: Erased

■ B110C with Standard white polyester

■ B110C with specific* polyester

*dedicated to solvent resistance

These performances are for guidance only. Results are obtained with adapted receiving material and optimum print conditions. (Ricoh test method)

IMS DIVISION

RICOH (THAILAND) LTD

341 Onnuj Road, Prawet, Prawet, Bangkok 10250, Thailand

Tel: 02-088-8888

Email: RTHIMS@Ricoh.co.th Website: www.ricoh.co.th

* Specifications are subjected to change without notice.

* The color(s) of the actual product may vary from the color(s) shown in this datasheet



Scan to visit product's page