

B120E

Premium

- Good heat resistance up to 110°C
- Applicable to a wide range of receiving labels: paper, coated paper, PET/PP/PE/PVC films.
- Ricoh's unique coating on the back allows reliable and superior matching qualities with the thermal head

PRINTING PROPERTIES

Maximum printing speed 10 IPS

For the characters: 1.0mm

Wax-Resin • Near Edge

	Non -coated paper	Coated paper	PET	PE	PP	PVC
Compatibility	Ś	Ś	$\overline{\mathbb{A}}$	$\overline{\mathbb{A}}$	Ś	Ś
Image density	1.85	1.85	1.74	2.05	1.80	1.87

Image resolution for paper:

Minimum size: For the lines: 0.2mm For the characters: 1.5mm

RIBBON PROPERTIES

- Total ribbon thickness: < 9 μ m
- Polyester film thickness: 4.5 μ m
- Friction coefficient: < 0.035

Minimum size: For the lines: 0.2mm

Tags Logistic/Storage Shipping

Application

Multi purpose

- Ink melting point: 84°C
- Tearing resistance: > 200N/mm²

Image resolution for film

• Transmission density: 1.00 mini

CERTIFICATES/ DIRECTIVES



GENERAL CONDITION


Usage conditions: 5 to 35°C at 30 to 85% of relative humidity. *Storage conditions*: Keep indoors avoiding high temperature, high humidity, and direct sunlight. *Storage life*: 24 months after production.

RICOH imagine. change.

PRINTED IMAGE DURABILITY

TESTS	RESULT
Smear + heat 30°C	ANSI A
Smear with cardboard	
(weight 1kg - 50 back & forwards)	
Heat (110°C)	No ink on the cotton fabric
Heat gradient 3.6kgF/cm ²	
Scratch	ANSI A
50 back and forwards with a rub tester	
Light	ANSI A
Xenon lamp at 650W/m²	
Water	ANSI A
24 hours in water	

B120E DURABILITY



These performances are for guidance only. Results are obtained with adapted receiving material and optimum print conditions. (Ricoh test method)

IMS DIVISION

RICOH (THAILAND) LTD

341 Onnuj Road, Prawet, Prawet, Bangkok 10250, Thailand Tel: 02-088-8888 Email: RTHIMS@Ricoh.co.th Website: www.ricoh.co.th

* Specifications are subjected to change without notice.

* The color(s) of the actual product may vary from the color(s) shown in this datasheet

